

CONIFLOOR 100

Two Component, Solvent Free Epoxy impregnation for cementitious substrates

Product description

CONIFLOOR 100 is a solvent free, very low viscosity, two component epoxy resin based impregnation.

Fields of application

CONIFLOOR 100 is designed for use as an impregnation on mineral substrates indoors such as concrete and cementitious screeds. It is suitable for use as a pore and capillary sealing

Properties

CONIFLOOR 100 has very low viscosity and therefore shows high capillary activity.

The material has very good adhesion to substrates based on minerals and / or cement. The impregnation can be all-purpose.

The yellowing which occurs when exposed to UV light does not impair its technical properties.

Fully cured, CONIFLOOR 100 exhibits very good mechanical properties. It is resistant to water, sea and waste water as well as to a variety of alkalis, diluted acids, brine, mineral oils, lubricants and fuels

Technical Data

Mixing ratio	Gewichtsteile Komp.	A : B	100 : 28
Density	Gemisch, bei 23 °C	g/cm ³	1,02
Viscosity	Gemisch, bei 23 °C	mPas	22
Working time (10 kg-working packs)	bei 10 °C	min.	150
	bei 20 °C	min.	80
	bei 30 °C	min.	40
Re-coating interval	bei 20 °C	minimal	h 12
		maximal	h 16
Ready for foot traffic	bei 10 °C	h	min. 24
	bei 20 °C	h	min. 12
	bei 30 °C	h	min. 6
Substrate and application traffic	minimal	°C	10
	maximal	°C	30
Max. permissible relative humidity		%	75
Trough-hardenend:	mech. resistance	bei 20 °C	d 5
	walkable	bei 20 °C	d 1
	chem. resistance	bei 20 °C	d 7
Tensile bond strength		N/mm ²	≥ 1,5

Diese Angaben sind Richtwerte. Die Werte dienen nicht zur Erstellung von Spezifikationen!

Application method

CONIFLOOR 100 is supplied in working packs which contain the correct proportions of component A (resin) and component B (hardener).

Mixing

Before mixing, precondition both A and B components to a **temperature** of approximately 15°C up to 25 °C.

Pour component B into component A and ensure that pail containing component B is emptied completely. Scrape the sides and the bottom of the pail several times to ensure complete mixing.

Do not mix by hand, **mix** with a **mechanical** drill and paddle at a very low speed (ca. 300 rpm) for **at 2 - 3 minutes**. Keep the mixer blades submerged in the material to **avoid** introducing air **bubbles**. Do not work out of the original drum / pail.

After proper mixing to a homogeneous consistency pour the mixture into a **fresh pail** and mix for another minute.

Consumption

The consumption of CONIFLOOR 100 used as primer is approximately between 0.1-0.15 kg/m² **depending** on the condition and porosity of the substrate.

A **2nd coat** of 0.1-0.15 kg/m² of **primer** CONIFLOOR 100 broadcasted can be necessary in order to close the capillar And the pores of the concrete

CONIFLOOR 100 should be applied when the ambient **temperature** is **constant** or falling as this will decrease the risk of bubble formation due to evaporation of air that is enclosed in the concrete. CONIFLOOR 100 is applied to the prepared substrate by rolling, spraying or spreading with a squeegee. **After** waiting for at least **10 minutes**, finish with a **roller**. Ponding or spots where the primer is applied thick have to be avoided.

Notes to the residues after working:

Due to the high reactive epoxy resin formulation, residues have to be filled with quarzsand. On 1 kg epoxyd-resin-mixture you have to fill about 3-4 kg quarzsand into it. After hardening the material has to be disposed.

At disregarding it will come to strong smoke- and heat development. Residues has to be stored outside

Temperatures

The working life and curing time of the material is influenced by the ambient, material and substrate temperatures. At low temperatures, the chemical reactions are slowed down; this lengthens the pot life, open time and curing times. High temperatures speed up the chemical reactions thus the time frames mentioned above are shortened accordingly.

To fully cure the material, substrate and application temperature should not fall below the minimum.

After application, the material should be protected from direct contact with water for approx. 24 h (at 20° C). Within this period, contact with water can cause a surface bloom

and/or surface tackiness, both of which must be removed else the adhesion to the following coating is impaired.

Substrate condition

All substrates (new and old) must be structurally sound, dry and free of laitance and loose particles. Clean floors of oil, grease, and rubber skid marks, paint stains and other adhesion impairing contaminants. The substrate must be dust-free (industry vaccum-cleaner)

After surface preparation the **tensile strength** of the concrete should exceed 1.0 N/mm² (check with an approved pull-off tester at a load rate of 100 N/s).

The **moisture level** of the sub-base needs to be **less** than **4 %**.

The **temperature** of the substrate must be at least **3 °C** above the current dew point temperature.

There must be a regular DPM between the stone base and the slab.

Cleaning agent

Re-usable tools should be cleaned carefully with CLEANER 44 or e.g. isopropanol.

Pack size

CONIFLOOR 100 is supplied in 10 kg working packs.

Colour

transparent

Storage

Store in original closed packing under dry conditions at a temperature range of 15 - 25 °C.

Do not expose the drums to direct sunlight.

Please check "best-before" date on the pail before usage.

Safety precautions

CONIFLOOR 110 is non-hazardous in its cured condition.

For protective measures, transport regulations and waste management please refer to the Material Safety Data Sheet of the product.

VOC Contents

CONIFLOOR 100 meets the requirements of the EC directive 2004/42/EC.



CE-Label:
See Declaration of Performance.

CONICA AG
Industriestrasse 26
8207 Schaffhausen
Suisse

Tel.: + 41 52 644 3600
Fax: + 41 52 644 3699
info@conica.com
www.conica.com

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the professional competence involved in the application of the product are beyond our control.

As all CONICA data sheets are updated on a regular basis, it is user's responsibility to obtain the most recent issue. Registered users can obtain the actual data sheets from our webpage. Hard copies are available upon request.