

CONIFLOOR 118

Fast and at low temperature curing, Two Component, Solvent Free Epoxy Primer

Product description

CONIFLOOR 118 is a solvent free, low viscosity, two component fast and at low temperature curing epoxy resin based primer.

Fields of application

CONIFLOOR 118 is designed for use as a primer on mineral substrates indoors and outdoors such as concrete and cementitious screeds.

It is suitable for use as a pore and capillary sealing. For this purpose the product is – after mixing of component A and B – filled with oven dried quartz sand.

The degree of filling depends on the temperatures as well as on the thickness of the layer and should be between 0.5 up to 1 for a scratch coat and up to 8 parts as a epoxy mortar referred to the primer (ratio by weight) .

Properties

CONIFLOOR 118 is solvent free and has very low viscosity and therefore shows high capillary activity. The primer cures in between a few hours and for this reduce the re-coating interval.

The material has very good adhesion to substrates based on minerals and / or cement. The primer can is all-purpose.

The yellowing which occurs when exposed to UV light does not impair its technical properties.

Fully cured, CONIFLOOR 118 exhibits very good mechanical properties. It is resistant to water, sea and waste water as well as to a variety of alkalis, diluted acids, brine, mineral oils, lubricants and fuels.

Technical Data

Mixing ratio	in parts by weight	A: B	100 : 40
Density	mix, at 23 °C	g/cm ³	1.11
Viscosity	mix, at 23 °C	mPas	750
Working time (25 kg working packs)	at 10 °C	min	20
	at 20 °C	min	10
	at 25 °C	min	5
Re-coating interval	at 10 °C	min. / max.	h 10 / 48
	at 23 °C	min. / max.	h 5 / 24
	at 25 °C	min. / max.	h 3 / 12
Ready for foot traffic	at 10 °C	h	min.10
	at 23 °C	h	min. 5
	at 25 °C	h	min. 3
Substrate and application temperature	minimum	°C	5
	maximum	°C	25
Max. permissible relative humidity		%	75
Shore D hardness	after 7 d		≥ 81
Tensile bond strength		N/mm ²	≥ 1.5

Above figures are guide values and should not be used as a base for specifications!

Application method

CONIFLOOR 118 is supplied in working packs which contain the correct proportions of component A (resin) and component B (hardener).

Mixing

Before mixing, precondition both A and B components to a **temperature** of approximately 15°C up to 25 °C.

Pour component B into component A and ensure that pail containing component B is emptied completely. Scrape the sides and the bottom of the pail several times to ensure complete mixing.

Do not mix by hand, **mix** with a **mechanical** drill and paddle at a very low speed (ca. 300 rpm) for **at 2 - 3 minutes**. Keep the mixer blades submerged in the material to **avoid** introducing air **bubbles**. Do not work out of the original drum / pail.

After proper mixing to a homogeneous consistency pour the mixture into a **fresh pail** and mix for another minute. Due to the fast curing property, we suggest to mix the two components as quickly as possible.

Consumption

The consumption of CONIFLOOR 118 used as primer is approximately between 0.3-0.5 kg/m² **depending** on the condition and porosity of the substrate.

A **2nd coat** of 0.2-0.4 kg/m² of **primer** CONIFLOOR 118 broadcasted with oven dried sand is **mandatory** in order to seal concrete pores and capillaries completely.

Unevenness \geq 0.5mm must be equalized by an additional scratch coat.

The above consumption figures are intended as a guide only and may be higher on very rough or porous substrates. For additional filling with fire dried silica sand grain size 0.1-0.3 mm is recommended.

CONIFLOOR 118 should be applied when the ambient **temperature** is **constant** or falling as this will decrease the risk of bubble formation due to evaporation of air that is enclosed in the concrete.

After mixing the two components of CONIFLOOR 118 the pail have to be empty and to treat the material immediately.

CONIFLOOR 118 is applied to the prepared substrate by rolling, spraying or spreading with a squeegee. **After** waiting for at least **3 minutes (at 20°C)**, finish with a **roller**. Ponding or spots where the primer is applied thick have to be avoided.

PUR Coatings

To improve the adhesion to a following coating oven dried **sand** (grain size 0.3-0.8mm – approx. 1kg/m²)) is **broadcasted** into the primer whilst still in order to improve adhesion of the following polyurethane based product. Bald patches as well as excess broadcasting have to be **avoided**.

Temperatures

The working life and curing time of the material is influenced by the ambient, material and substrate temperatures. At low temperatures, the chemical reactions are slowed down; this lengthens the pot life, open time and curing times. High temperatures speed up the chemical reactions thus the time frames mentioned above are shortened accordingly.

To fully cure the material, substrate and application temperature should not fall below the minimum.

After application, the material should be protected from direct contact with water for approx. 12 h (at 20° C). Within this period, contact with water can cause a surface bloom and/or surface tackiness, both of which must be removed else the adhesion to the following coating is impaired.

Substrate condition

All substrates (new and old) must be structurally sound, dry and free of laitance and loose particles. Clean floors of oil, grease, and rubber skid marks, paint stains and other adhesion impairing contaminants.

A pre-treatment of the substrate by grit or shot blasting, high pressure water jetting, grinding or scabbing including the necessary post-treatment is only necessary, when the layer is soiled or the re-coating intervals have been exceeded.

After surface preparation the **tensile strength** of the concrete should exceed 1.5 N/mm² (check with an approved pull-off tester at a load rate of 100 N/s).

The **moisture level** of the sub-base needs to be **less** than 4 %.

The **temperature** of the substrate must be at least **3 °C** above the current dew point temperature.

There must be a regular DPM between the stone base and the slab.

Cleaning agent

Re-usable tools should be cleaned carefully with CLEANER 44 or e.g. isopropanol.

Pack size

CONIFLOOR 118 is supplied in 10 kg working packs.

Colour

transparent

Storage

Store in original closed packing under dry conditions at a temperature range of 15 - 25 °C.

Do not expose the drums to direct sunlight.

Please check "best-before" date on the pail before usage.

Safety precautions

CONIFLOOR 118 is non-hazardous in its cured condition.

For protective measures, transport regulations and waste management please refer to the Material Safety Data Sheet of the product.

VOC Contents

CONIFLOOR 118 meets the requirements of the EC directive 2004/42/EC.



CE-Label:

See Declaration of Performance.

CONICA AG
Industriestrasse 26
8207 Schaffhausen
Suisse

Tel.: + 41 52 644 3600
Fax: + 41 52 644 3699
info@conica.com
www.conica.com

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the professional competence involved in the application of the product are beyond our control.

As all CONICA data sheets are updated on a regular basis, it is user's responsibility to obtain the most recent issue. Registered users can obtain the actual data sheets from our webpage. Hard copies are available upon request.