

# CONIFLOOR 431 AS SR

Total solid, filled with SIC, pigmented, hard and tough two component, Antistatic, epoxy-based textured hard grain coating

## Product description

CONIFLOOR 431 AS SR is a two component, solvent free, self-levelling, pigmented, hard, tough and resistant epoxy hard grain coating.

## Fields of application

CONIFLOOR 431 AS SR is used as a structured coating and used as a coating on mineral, primed (with CONIFLOOR 110 and CONIFLOOR 150) substrates for indoor floorings with low to medium mechanical strain, where anti-static properties are required.

CONIFLOOR 431 AS SR is used in the indoor flooring system CONIFLOOR IET AS SR.

## Properties

CONIFLOOR 431 AS SR exhibits high mechanical properties, resistant to abrasion and is easy to apply.

CONIFLOOR 431 AS SR is easy to clean and resistant to water, sea and waste water, a variety of alkaline substances, diluted acids, brine, mineral oils, lubricants and fuels.

The yellowing which occurs when CONIFLOOR 431 AS SR is exposed to UV light does not affect its mechanical properties.

## Technical Data

<b>Mixing ratio</b>	in parts by weight			100:14,3
<b>Density</b>	mix,	at 23 °C	g/cm <sup>3</sup>	1.63
<b>Viscosity</b>	mix,	at 23 °C	mPas	thixotropic
<b>Processing time</b>	at 10°C		min. approx.	40
	at 20°C		min. approx.	30
	at 30°C		min. approx.	20
<b>Re-coating interval / ready for foot traffic</b>	at 20 °C		minimum h	14
			maximum h	48
<b>Substrate and application temperature</b>	minimum		°C	10
	maximum		°C	30
<b>Permissible relative humidity</b>	maximum		%	75
<b>Ready for</b>	<b>mech. strain</b>	at 20 °C	d	3
	<b>light mech. strain</b>	at 20 °C	d	1
	<b>chem. strain</b>	at 20°C	d	7
<b>Shore D hardness</b>	after 28 d			80
<i>Above figures are guide values and should not be used as a base for specifications!</i>				

### Application method

CONIFLOOR 431 AS SR is supplied in the correct proportions of component A (resin) and component B (hardener). Pour component B into component A and ensure that the pail containing component B is emptied completely.

To achieve a homogenous mix, thoroughly mix with a slowly rotating mixing device at about 300 rev/min. Ensure that the mixing device reaches side and bottom areas of the mixing vessel. The mixing process takes at least 2 to 3 minutes and should be performed until the blend is homogenous and streak free.

Pour the mix into another clean pail and mix it again for min. 2 additional minutes.

The temperature of the components should be between 15-25 °C.

CONIFLOOR 431 AS SR can then be applied directly to the pre-treated substrate.

CONIFLOOR 431 AS SR is applied using the mixture is poured onto the prepared substrate and then levelled over the grain with a smoothing trowel.

Work the surface over with a suitable textured roller and then pass again moving in on direction and without applying pressure with another textured roller.

Working life and curing time of CONIFLOOR 431 AS SR are influenced by the ambient and substrate temperature. At low temperatures, the chemical reactions are slowed down; this lengthens the pot life, re-coating interval and open time. High temperature and humidity accelerate chemical reactions so the contrary is true.

To fully cure the material, the substrate and working temperature must not fall below the minimum.

After application, the material should be protected from direct contact with water for approx. 24 hours (at min. 15 °C). Within this period, contact with water can cause white discoloration and carbamate formation on the surface of the coating.

The relative humidity level may not exceed 75%.

### Consumption

The consumption rate of CONIFLOOR 431 AS SR is min. 680 g/m<sup>2</sup> up to max. 800 g/m<sup>2</sup>.

### Cleaning agent

Re-usable tools should be cleaned carefully with CLEANER 44 or e.g. isopropanol.

### Substrate condition

Cement bound substrates to be coated must be firm, dry, load bearing and free of loose and brittle particles and substances, which impair adhesion such as oil, grease, rubber skid marks, paint or other contaminants.

A pre-treatment of the substrate by grit or shot blasting, high pressure water jetting, grinding or scabbing including the necessary post-treatment is mandatory.

After the pre-treatment the bond strength of the concrete must be at least 1.5 N/mm<sup>2</sup>.

The moisture level must not exceed 4 %.

The temperature of the substrate must be at least 3°C above the current dew point temperature.

The sub base must contain a moisture barrier (damp proof membrane D.P.M.).

After the pre-treatment the bond strength of the concrete must be at least 1.5 N/mm<sup>2</sup>.

### Pack size

CONIFLOOR 431 AS SR is supplied in 33.6 kg (metal) working packs. Components A and B are supplied in the correct proportions and delivered separately.

### Colour

Colours upon request.

### Storage

Store in unopened pails under dry conditions at a temperature range of 5-25 °C.

Do not expose to direct sunlight.

Before use, please see "best before" date on the pail / drum.

### Safety precautions

CONIFLOOR 431 AS SR is non-hazardous in its cured condition.

For protective measures, transport regulations and waste management please refer to the Material Safety Data Sheet of the product.

### VOC contents

CONIFLOOR 431 AS SR meets the requirements of the EC directive 2004/42/EC.



### CE-Label:

See Declaration of Performance.

CONICA AG  
Industriestrasse 26  
professional  
8207 Schaffhausen  
Suisse  
Tel.: + 41 52 644 3600  
Fax: + 41 52 644 3699  
[info@conica.com](mailto:info@conica.com)  
[www.conica.com](http://www.conica.com)

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence involved in the application of the product are beyond our control.

*As all CONICA data sheets are updated on a regular basis, it is user's responsibility to obtain the most recent issue. Registered users can obtain the actual data sheets from our webpage. Hard copies are available upon request.*