

CONIFLOOR 111

Two part Polyaspartic resin, fast curing primer and even at low temperatures, low solvent content

Product description

CONIFLOOR 111 is a two-component Polyaspartic resin based primer, fast curing and reacts at low temperatures with low solvent content.

Fields of application

CONIFLOOR 111 is designed for use as a primer on mineral substrates indoors and outdoors such as concrete and cementitious screeds.

Properties

CONIFLOOR 111 has a low viscosity and therefore shows high capillary activity.

The material has very good adhesion to substrates based on minerals and / or cement. The primer can be all-purpose.

The yellowing, which occurs when exposed to UV light, does not impair its technical properties.

Fully cured, CONIFLOOR 111 exhibits very good mechanical properties. It is resistant to water, sea and wastewater as well as to a variety of alkalis, diluted acids, brine, mineral oils, lubricants and fuels.

Technical Data

Mixing ratio	in parts by weight	A: B	100 : 50
Density	mix, at 23 °C	g/cm ³	1.4
Viscosity	mix, at 23 °C	mPas	1000
Working time (25 kg working packs)	at 20 °C	min	30
Re-coating interval	at 20 °C	min.	h
		max.	h
Ready for foot traffic	at 10 °C	h	min. 1-2
	at 23 °C	h	min. 1
Substrate and application temperature	minimum	°C	3
	maximum	°C	28
Max. permissible relative humidity		%	75
Shore D hardness	after 7 d		60
Tensile bond strength		N/mm ²	≥ 1.5
<i>Above figures are guide values and should not be used as a base for specifications!</i>			

Application method

CONIFLOOR 111 is supplied in working packs, which contain the correct proportions of component A (resin) and component B (hardener).

Pour component B into component A and ensure that pail containing component B is emptied completely. Scrape the sides and the bottom of the pail several times to ensure complete mixing.

Mixing

Before mixing, precondition both A and B components to a [temperature](#) of approximately 15°C up to 25 °C.

Do not mix by hand, mix with a **mechanical** drill and paddle at a very low speed (ca. 300 rpm) for **at 2 - 3 minutes**. Keep the mixer blades submerged in the material to **avoid** introducing air **bubbles**. Do not work out of the original drum / pail.

After proper mixing to a homogeneous consistency, pour the mixture into a **fresh pail** and mix for another minute.

Consumption

The consumption of CONIFLOOR 111 used as primer is approximately between 0.4-0.5 kg/m² **depending** on the condition and porosity of the substrate.

A **2nd coat** of 0.2-0.4 kg/m² of **primer** CONIFLOOR 111 broadcasted with oven-dried sand is **mandatory** in order to seal concrete pores and capillaries completely.

Unevenness >0.5mm must be equalized by an additional scratch coat.

CONIFLOOR 111 should be applied when the ambient **temperature** is **constant** or falling, as this will decrease the risk of bubble formation due to evaporation of air that is enclosed in the concrete.

CONIFLOOR 111 is applied to the prepared substrate by rolling, spraying or spreading with a squeegee. **After** waiting for at least **10 minutes**, finish with a **roller**. Ponding or spots where the primer is applied thick have to be avoided. **Less thickness accelerates the curing and higher thickness slows down the curing.**

PUR Coatings

To improve the adhesion to a following coating oven dried **sand** (grain size 0.3-0.8mm – approx. 1kg/m²) is **broadcasted** into the primer whilst still in order to improve adhesion of the following polyurethane based product. Bald patches as well as excess broadcasting have to be **avoided**.

Temperatures

The ambient, the thickness, and material and substrate temperatures influence the working life and curing time of the material. At low temperatures, the chemical reactions are slowed down; this lengthens the pot life, open time and curing times. High temperatures speed up the chemical reactions thus the periods mentioned above are shortened accordingly.

To fully cure the material, substrate and application temperature should not fall below the minimum.

After application, the material should be protected from direct contact with water for approx. 12 h (at 20° C). Within this period, contact with water can cause a surface bloom and/or surface tackiness, both of which must be removed else the adhesion to the following coating is impaired.

Substrate condition

All substrates (new and old) must be structurally sound, dry and free of laitance and loose particles. Clean floors of oil, grease, and rubber skid marks, paint stains and other adhesion impairing contaminants.

A pre-treatment of the substrate by grit or shot blasting, high-pressure water jetting, grinding or scabbing including the necessary post-treatment is only necessary, when the layer is soiled or the re-coating intervals have been exceeded.

After surface preparation, the **tensile strength** of the concrete should exceed 1.5 N/mm² (check with an approved pull-off tester at a load rate of 100 N/s).

The **moisture level** of the sub-base needs to be **less than 4 %**.

The **temperature** of the substrate must be at least **3 °C** above the current dew point temperature.

There must be a regular DPM between the stone base and the slab.

Cleaning agent

Re-usable tools should be cleaned carefully with CLEANER 40 or e.g. Xylene.

Pack size

CONIFLOOR 111 is supplied in 25 kg and 10 kg working packs.

Colour

Beige

Storage

Store in original closed packing under dry conditions at a temperature range of 15 - 25 °C.

Do not expose the drums to direct sunlight.

Please check "best-before" date on the pail before usage.

Safety precautions

CONIFLOOR 111 is non-hazardous in its cured condition.

For protective measures, transport regulations and waste management please refer to the Material Safety Data Sheet of the product.

VOC Contents

CONIFLOOR 111 meets the requirements of the EC directive 2004/42/EC.



CE-Label:

See Declaration of Performance.