


# CONIPUR CE *pure* Full PUR

Low Emission Combined-Elastic Indoor Sports Surfacing System with Liquid Foam Mat as Elastic Layer

Fields of application

multipurpose sports halls

System data

		Product	Consumption	Application	Remarks
Spreading plate	or	<b>Wooden matrix glue</b>	25 - 50 mm approx. 40 g/m <sup>2</sup>	Tongue and groove gluing	The wooden sub base construction as well as the glue must be approved by CONICA. Moisture content of the wood < 7 %. Humidity during the installation must be between 35 - 65 %. Before the application process, the surface must be grinded and cleaned thoroughly.
		<b>CONIPUR WBI</b> wooden matrix, 15 + 15 mm	<i>System build-up and information on the installation please see separate system data sheet</i>		
		<i>grinding of the wooden surface and subsequent vacuuming is necessary in any case</i>			
Primer		<b>CONIPUR 3710</b>	0.1 - 0.2 kg/m <sup>2</sup>	rubber squeegee	The primer is necessary to prevent any detachment of the subsequent PUR layer.
Elastic Layer		<b>CONIPUR 3335</b>	3.0 kg/m <sup>2</sup> = 4mm 4.5 kg/m <sup>2</sup> = 6mm	pin squeegee	This corresponds to a consumption of 0.75 kg/m <sup>2</sup> .  The elastic layer is normally 4 or 6mm thick.  To avoid a running-off of the coating at the edges, a self-gluing <b>foam strip</b> is fixed on the wood along the edges.
		To mix the product a <b>double head stirrer</b> is most suitable – for large surfaces 2 agitating tools must be used to ensure a smooth installation  After curing, the coating can be coated (within the recoating interval) without further preparation			
Coating	Top layer	<b>CONIPUR 224 (N)</b>	2.6 kg/m <sup>2</sup> = 2mm 3.9 kg/m <sup>2</sup> = 3mm thickness	notched squeegee	
Sealing lacquer		<b>CONIPUR 3202 W</b>	0.13 – 0.15 kg/m <sup>2</sup>	Paint roller	Critical colours regarding coverage must repeatedly be applied until opacity is achieved.  Critical colours with respect to staining must be fixed with a transparent sealing lacquer.
					
Line Paint		<b>CONIPUR 3100</b>	15 g/m	Paint roller (paint-brush)	Critical colours regarding coverage must be applied twice.

Total thickness of the system

x + 2 mm, x = thickness of the wooden matrix system (15+15 mm) and the **point elastic** layer (recommended 4 – 6 mm)

## Selected technical properties

		Thickness in mm (sub base+ coating)	Result	Requirement	Remarks
in accordance with EN 14904	Shock absorption	approx. 36 mm	60 %	Type 3: ≥45 <55 % Type 4: ≥55 <75 %	Results taken from test report
	Standard deformation	approx. 36 mm	3.9 mm	Type 3: ≥1.8 <5,0 (mm) Type 4: ≥2.3 <5.0 (mm)	
	Rolling load	approx. 36 mm	1500 Nm	1500 Nm	
	Ball rebound	approx. 36 mm	99 %	≥ 90 %	
	Abrasion	approx. 36 mm	20 mg	max. 80 mg (sealer)	
	Sliding properties	approx. 36 mm	95	80-110	
	Resistance to impact	approx. 36 mm	19	≥ 8	
	Residual impression	approx. 36 mm	0.06 %	≤ 0.5 mm	

All technical details have been taken from test certificates and refer to the main products only. Depending on the substrate, conditions of application and usage of alternative products the values may change.

### test reports / certificates available

#### emission / VOC



#### Declaration of Performance



\*Please see our web-page or contact our Technical Service to obtain country specific test reports / test certificates.

### Preparation

Substrates to be coated have to be firm, dry and load bearing, free of loose and brittle particles and substances, which impair adhesion such as oil, grease, rubber skid marks, paint or other contaminants.

A concrete sub base must contain a moisture barrier (damp proof membrane D.P.M.). The **residual moisture** of the **subbase** must not exceed **4 %**.

The **temperature** of the substrate must be at least **3 °C** above the current dew point temperature.

With regard to the **flatness** of the subfloor, we refer to the DIN 18202, 2005-10 Table 3, line 4.

The optimal **temperature** of the material before and during application is between **15** and **25 °C**.

### Application

#### Elastic layer

Underneath the wooden sub-base, an **elastic layer** of approx. **15 mm** (e.g. foam mat) must be installed. The foam mat must be fixed pointwise to prevent it from moving.

On top of the foam mat, a foil made of polyethylene is laid over the complete floor. The foil serves as protection of the foam mat and facilitates the working with the wooden plates.

#### Distribution plate

Beginning with the first line of the load distribution plate the groove-side has to be orientated to the wall. The distance to the wall should be ensured by installing **spacer blocks** with 15 mm thickness.

After laying the surface, the spacer blocks have to be removed, the edge distance must be maintained to the ground to provide a possibility for the floor to expand.

The **expansion joints** must be guaranteed for long term.

The second line of the load distribution plate begins with the remaining piece of the first line. The **offset** amount should be minimum 400 to maximum 500 mm (if not possible cut a new element). The other rows of the load distribution plates are carried out analogously.

The **position of the sleeves** has to be marked clearly on the distribution plate and cut out afterwards.

The load distribution plates are **glued** together in the tongue and groove connection. After the application, the load distribution plates are pressed thoroughly together.

The **curing time** of the glue is approximately 24 hours. During that time, the floor must not be loaded.

The surface has to be **ground** and **vacuumed** before the next step

**Point elastic layer**

CONIPUR 3710 is applied to the prepared wood using a rubber squeegee.

To avoid a running-off of the coating, a self-gluing **foam strip** is fixed onto the wood along the edges.



After that, CONIPUR 3335 is applied with a pin squeegee.

The pin squeegee should be set 1-2mm higher than the desired layer.



After overnight cure, CONIPUR 224 (N) is applied using a notched trowel or squeegee.

The **over-coating interval of 72 hours** must not be exceeded. CONIPUR 3335 can not be ground, else the surface will be destroyed. Small failures need to be cut and pore sealed with CONIPUR 220.

Seal the surface with CONIPUR 3202 W which is applied by **rolling** with "Microtex" rollers (tuft size 10 - 12 mm). Roll out well and keep the **overlap** areas to a **minimum**. It is necessary to **re-roll** freshly applied material with a second clean paint roller in order to obtain a uniform surface with a minimum of overlap marks

It is necessary to **re-roll** freshly applied material with a spurned clean paint roller in order to obtain a uniform surface with a minimum of overlap marks.

**Remarks**

For application conditions please see our "General Application Guidelines for Sports Systems Indoor and Outdoor".

For further information, please refer to the technical data sheets of the products or contact our Technical Service.

**CE marking only when installed according to system data sheet**

**CONIPUR CE pure FULL PUR**



CONICA AG, Industriestr. 26, 8207 Schaffhausen, Switzerland

17

**SY/CE/FP1/2017**

EN 14904:2006

combined-elastic, low emission indoor sports flooring surface

**CONIPUR CE pure FULL PUR**

EN 14904: E<sub>fl</sub> – 20 mg – 95 – 60 % - 1500N – E1

Essential characteristics	Performance	Harmonised technical specification
<b>Reaction to fire</b>	E <sub>fl</sub>	EN 14904:2006
<b>Resistance to wear</b>	20 mg	EN 14904:2006
<b>Friction</b>	95	EN 14904:2006
<b>Force reduction</b>	60 %	EN 14904:2006
<b>Rolling load without damage</b>	1500N	EN 14904:2006
<b>Release of dangerous substances</b>	class E1	EN 14904:2006