

CONIPROOF EP 190/1 (old CONIPROOF 190/1)

Two part EP resin primer for cementitious substrates also with increased moisture content, (total solid)

Product description

CONIPROOF EP 190/1 is a two component, [unpigmented epoxy](#) resin primer, "Total Solid accord. to the test methods Deutsche Bauchemie e.V." and ready to use on mineral substrates indoors and outdoors such as concrete and cementitious screeds.

CONIPROOF EP 190/1 can also be used at elevated residual moisture content and on substrates with the risk of rising moisture.

Fields of application

CONIPROOF EP 190/1 is part of the car park system CONIPROOF PES, CONIPROOF HYBRID OS8, CONIPROOF PPC DL and CONIPROOF PPC SL and [tested according to EN 1504-2 for surface protection](#). It is suitable for use as a pore and capillary sealing for this purpose the product is – after mixing of component A and B – filled with oven-dried silica sand. It is also [tested for higher residual moisture content](#) on concrete surfaces.

Properties

CONIPROOF EP 190/1 has low viscosity and therefore shows high capillary activity.

The material has very good adhesion to substrates based on minerals and / or cement. The primer can be used in universal applications and [also as blocking primer](#).

Fully cured, CONIPROOF EP 190/1 exhibits very good mechanical properties. It is resistant to water, sea and wastewater as well as to a variety of alkalis, diluted acids, brine, mineral oils, lubricants and fuels.

CONIFLOOR 190/1 is used in following systems:

- CONIPROOF PES
- CONIPROOF PPC SL
- CONIPROOF PPC DL
- CONIPROOF HYBRID OS8 and others

Technical Data

Mixing ratio	in parts by weight	A: B	100 : 43
Density	mix, at 23 °C	g/cm ³	1.09
Viscosity	mix, at 23 °C	mPas	430
Working time (25 kg working packs)	at 10 °C	min	60
	at 20 °C	min	30
	at 30 °C	min	15
Re-coating interval	at 20 °C	min.	h 8
		max.	h 48
Ready for foot traffic	at 10 °C	h	min. 24
	at 23 °C	h	min. 8
	at 30 °C	h	min. 4
Substrate and application temperature	minimum	°C	10
	maximum	°C	30
Max. permissible relative humidity		%	75
Tensile bond strength		N/mm ²	≥ 1.5

Above figures are guide values and should not be used as a base for specifications!

Application method

Please also [note the information in our general processing guidelines](#).

CONIPROOF EP 190/1 is supplied in working packs, which contain the correct proportions of component A (resin) and component B (hardener).

Mixing

Before mixing, precondition both A and B components to a [temperature](#) of approximately 15°C up to 25 °C.

Pour component B into component A and ensure that pail containing component B is emptied completely. Scrape the sides and the bottom of the pail several times to ensure complete mixing. Do not mix by hand, [mix](#) with a [mechanical](#) drill and paddle at a very low speed (ca. 300 rpm) for [at 2-3 minutes](#). Keep the mixer blades submerged in the material to [avoid](#) introducing air [bubbles](#). Do not work out of the original drum / pail.

After proper mixing to a homogeneous consistency, pour the mixture into a [fresh pail](#) and mix for another minute.

CONIPROOF EP 190/1 should be applied when the ambient [temperature](#) is [constant or falling](#), as this will decrease the risk of bubble formation due to evaporation of air that is enclosed in the concrete.

CONIPROOF EP 190/1 is applied to the prepared substrate by rolling or spreading with a rubber squeegee. [After](#) waiting for at least [10 minutes](#), finish with a [roller](#). Ponding or spots where the primer is applied thick have to be avoided.

Consumption

The consumption of CONIPROOF EP 190/1 used as primer or scratch primer is minimum [0.3-0.5 kg/m²](#) [depending](#) on the condition and porosity of the substrate.

When used as [blocking primer](#) or with [increased residual moisture](#) up to max. 6 % by weight, the first application must be carried out [film-forming](#) with [min. 0.5 - 0.7 kg/m²](#). The [1st](#) blocking primer is [not broadcasted](#) and recoated within the recoating interval with a second operation.

A [2nd](#) coat of [0.2-0.4 kg/m²](#) of primer CONIPROOF EP 190/1 is [mandatory](#) in order to seal concrete pores and capillaries completely.

The re-coating interval at +20°C is max. 24h. The first layer of primer [isn't broadcasted](#) with sand within the mentioned interval.

Unevenness $\geq 0.5\text{mm}$ must be equalized general by an additional scratch coat.

CONIFLOOR 190/1 is suitable for use as a pore and capillary sealing for this purpose the product is – after mixing of component A and B – filled with oven-dried silica sand.

The [degree](#) of filling [depends](#) on the temperatures as well as on the thickness of the layer and should be between 0.5 up to 1.5 referred to the primer (ratio by weight).

The above consumption figures are intended as a guide only and may be higher on very rough or porous substrates.

PUR Coatings

To improve the adhesion to a following coating oven dried [sand](#) (grain size 0.3-0.8 mm – approx. 0.8 – 1.0 kg/m²) is [broadcasted](#) into the primer whilst still in order to improve adhesion of the following polyurethane based product.

Bald patches as well as excess broadcasting have to be [avoided](#).

Temperatures

The ambient, material and substrate temperatures influence the working life and curing time of the material. At low temperatures, the chemical reactions are slowed down; this lengthens the pot life, open time and curing times. High temperatures speed up the chemical reactions thus the periods mentioned above are shortened accordingly.

To fully cure the material, substrate and application temperature should not fall below the minimum.

After application, the material should be protected from direct contact with water for approx. 24 h (at 20° C). Within this period, contact with water can cause a surface bloom and/or surface tackiness, both of which must be removed else the adhesion to the following coating is impaired.

Cleaning agent

Re-usable tools should be cleaned carefully with CLEANER 44 or e.g. isopropanol.

Substrate condition

The subsurface (old and new) must be structurally sound, solid, free of loose particles and laitance, dust, oils, greases, rubber abrasion and other separating substances. The surface tensile strength of the surface to be primed must be at least 1.5 N/mm² (smallest individual value at least 1.0 N/mm²), the compressive strength at least 25 N/mm². The substrates must have reached their equilibrium moisture content and also be protected from the effects of rising water during use or special measures must be taken, such as applying an additional blocking primer (ask our technical service).

Concrete	max. 4 M-% moisture
Cement screed	max. 4 M-% moisture
2-fold, film-forming primer up to max. 6 M-% moisture (after consultation with technical service)	

There must be a regular damp proof membrane (DPM) between the stone base and the slab. The occurrence of moisture penetration on the rear side must be impossible.

The [temperature](#) of the substrate must be at least [3 °C](#) above the current dew point temperature.

There must be a regular DPM between the stone base and the slab.

Pack size

CONIPROOF EP 190/1 is supplied in 25 kg working packs.

Colour

Transparent

Storage

Store in original closed packing under dry conditions at a temperature range of 15 - 25 °C.

Do not expose the drums to direct sunlight.

Please check "best-before" date on the pail before usage.

Safety precautions

CONIPROOF EP 190/1 is non-hazardous in its cured condition.

For protective measures, transport regulations and waste management please refer to the Material Safety Data Sheet of the product.

VOC Contents

CONIPROOF EP 190/1 meets the requirements of the EC directive 2004/42/EC.

The limit value for products ready for use (product type according to table IIA j Type sb) is:

Level II (from 2010) <500 g/l VOC.

When ready to use, this product contains less than 500 g/l VOC.



CE Declaration of Performance

CE-Mark according to EN 1504-2

Products and systems for the protection and repair of concrete structures - Definitions, requirements, quality control and evaluation of conformity - Part 2: Surface protection products and systems for concrete.

Details see CE-conformity mark and conformity declaration.

CE-Mark according to EN 13813

EN 13813: 2003-01, Screed material and floor screeds - Screed materials - Properties and requirements is the basis for requirements for floor screeds used in indoor flooring constructions. Resin coatings and sealer are also subject to this norm.

Details see CE-conformity mark and conformity declaration.

CONICA AG
Industriestrasse 26
8207 Schaffhausen
Suisse

Tel.: + 41 52 644 3600
Fax: + 41 52 644 3699
info@conica.com
www.conica.com

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the professional competence involved in the application of the product are beyond our control.

As all CONICA data sheets are updated on a regular basis, it is user's responsibility to obtain the most recent issue. Registered users can obtain the actual data sheets from our webpage. Hard copies are available upon request.